# Erosion-Corrosion Resistant Metal Repair Composite





Belzona 1311 (Ceramic R-Metal) is a repair composite designed for rebuilding and protecting metal against the effects of erosion and corrosion.

This cold-applied material benefits from excellent erosion resistance and can be used to restore equipment operating under immersion without the need for hot work.

Belzona 1311 demonstrates outstanding adhesion to a variety of substrates, allowing it to also be used as a high strength structural adhesive for metal bonding. For longlasting performance, it can be overcoated with another of Belzona's 1300 Series materials.

DNVGL



1½ days

3 days



| TECHNICAL DATA | Mixing ratio (base:solidifier) | 3 : 1 by volume                          |             | 5 : 1 by weight                    |                                       |  |
|----------------|--------------------------------|--|-------------|------------------------------------|---------------------------------------|--|
|                | Working life                   | 15 minutes at 25°C (77°F)                |             |                                    |                                       |  |
|                | Shelf life                     | 5 years                                  |             |                                    |                                       |  |
|                | Dry heat resistance            | 200°C (392°F)                            |             |                                    |                                       |  |
|                | Adhesion (tensile shear )      | Mild steel: 20.7 MPa (3,000 psi)         |             | Stainless steel:                   | Stainless steel: 19.0 MPa (2,760 psi) |  |
|                | Compressive strength (yield)   | 56.8 MPa (8,235 psi) at 20°C (68°F) cure |             |                                    |                                       |  |
|                | Volume capacity                | 415 cm³ (25.3 in³) / 1 kg                |             | 830 cm³ (50.6                      | 830 cm³ (50.6 in³) / 2 kg             |  |
|                | Heat distortion temperature    | 51°C (124°F) at 20°C (68°F) cure         |             | 89°C (192°F) at 100°C (212°F) cure |                                       |  |
|                | Abrasion resistance            | H10 - 194 mm <sup>3</sup> wet            |             | CS17 - 25 mm <sup>3</sup> dry      |                                       |  |
|                |                                |  |             |                                    |                                       |  |
| IMES           | Temperature                    | 10°C (50°F)                              | 15°C (59°F) | 20°C (68°F)                        | 25°C (77°F)                           |  |
|                | No loading or immersion        | 3 hours                                  | 2½ hours    | 1 ¾ hours                          | 1 hour                                |  |
| H              | Machining and/or light loading | 4 hours                                  | 3 hours     | 2 hours                            | 1½ hours                              |  |

2 days

4 days

\*Please consult the Product Specification Sheet (PSS) and Instructions for Use (IFU) for the latest technical data.



Full mechanical or thermal loading

Immersion in chemicals

EROSION RESISTANT



CORROSION RESISTANT



CHEMICAL RESISTANT



1 day

2 days

EXCELLENT ADHESION



20 hours

1½ day

SOLVENT FREE

## <mark>1000 Series</mark> BELZONA 1311



## Key Benefits:

### • Erosion-corrosion resistance

This metal repair composite offers outstanding erosion and corrosion resistance.

### • Excellent adhesion

Belzona 1311 demonstrates excellent adhesion to a variety of metallic substrates.

### • Chemical resistance

Belzona 1311 is resistant to a variety of chemicals, including hydrocarbons and process chemicals.

### Solvent free

This solvent-free solution does not shrink when curing and reduces health and safety risks in confined spaces.





### **Application Areas:**

### • Rebuilding metal loss

This metal repair composite can reverse the effects of metal loss on equipment and protect against further erosion.

### • Equipment under immersion

Belzona 1311 can be used to repair equipment operating under immersion, including pumps and HVAC systems.

### • High-strength structural adhesive

The adhesive strength of Belzona 1311 makes it suitable for use as a structural adhesive and for cold bonding purposes.

### • Load bearing shims

Belzona 1311 can be used to create load bearing shims as it will not shrink.

For more information, please contact your local Belzona representative:

#### QUALITY PRODUCTS - TECHNICAL SUPPORT

Belzona products are manufactured under an ISO 9001 Registered Quality Management System.

Belzona has a global distribution network of over 140 Distributors operating in 120 countries. Local support is provided by a trained Technical Consultant who will diagnose the problem, recommend the solution and provide 24-hour, on-site application supervision and advice.